

++++
 +++ Post's Great White +++
 +++
 This glaze comes from <http://www.johnpost.us>

Range: Cone 1-3
 Firing type: 2020 degrees F
 Date: 08/04/14

Borax	200	2 %
EPK	1800	18 %
Kentucky OM #4	700	7 %
Gerstley borate	1000	10 %
Frit 3110	1600	16 %
Flint	2500	25 %
Nepheline syenite	1300	13 %
Whiting	900	9 %
	-----	-----
	10000	100 %

=====
 Chemical Analysis
 =====

Na2O	0.31	Al2O3	0.52	SiO2	3.91
K2O	0.04	B2O3	0.24	TiO2	0.01
MgO	0.04			Fe2O3	0.00
CaO	0.60				

Alumina:Silica ratio is 1.00 : 7.57
 Neutral:Acid ratio is 1.00 : 5.19
 Alkali:Neutral:Acid ratio is 1.00 : 0.75 : 3.92

Expansion coefficient: 71.8 x 10e-7 per degree C